

# Seaming Tape LMP Grade

Fabric/Polyethylene Film Laminate

## INTRODUCTION

Sport-Fix Seaming Tape LMP is a specially constructed tape for use with the recommended Sport-Fix Adhesive in forming strong bonds when seam jointing artificial sand-filled carpets used in the surfacing of sports areas.

The tape consists of a strong geo textile fabric on one side and this is laminated to a Polyolefinic film to prevent the penetration of adhesive through to the under surface. Sport-Fix Seaming Tape LMP is for use with medium to long pile carpets.

## FEATURES

- Impervious to moisture ingress from the base.
- Strong rot proof geo textile bonding medium.
- Lays flat to substrate when rolled out.
- Film backed to prevent adhesive penetrating to base.

## METHOD OF USE

IMPORTANT: Before embarking on any work involving Sport-Fix Seaming Tape LMP the Health and Safety Data Sheet should be carefully studied by those carrying out the work.

## APPLICATION

Sport-Fix Seaming Tape LMP is designed for use mainly with Sport-Fix Multi Purpose Polyurethane Adhesive. It is constructed to form strong bonds to medium or long pile artificial sand filled carpets when used with this adhesive. The correct amount of EnviroStik Adhesive is applied by notched applicator to the fabric side of the tape and the edges of the carpet are pressed into the wet adhesive. For more detailed instructions on the use of this product see the Data Sheet for Sport-Fix Multi Purpose Adhesive.

## PRODUCT CHARACTERISTICS

Colour & Form:	White geo textile/transparent film laminate.
Bonding Medium:	Non-woven Polyester geo textile.
Backing Medium:	Modified Polyolefin film.
Roll Size:	Length: 300 m. Width: 30 cm, 40 cm and 50 cm. (Other widths slit to order)
Thickness:	0.50 - 0.54 mm.
Weight:	170 g/m <sup>2</sup> .
Tensile Strength:	400 N/5 cm.
Temperature Stability:	-25°C to +70°C.
Storage:	0 to 30°C.
Packaging:	Rolls individually film wrapped, and palletised for transport.

This leaflet is for general guidance only and may contain inappropriate information under particular conditions of use. The company cannot accept any responsibility for loss or damage that may result from the use of this information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm the suitability of this product by their own tests.